

Process for the production of nickel hydroxides**A b s t r a c t**

A process is described for the production of spherical nickel hydroxide by anodic dissolution of a nickel electrode and precipitation of nickel hydroxide in a completely intermixed electrolysis cell, wherein an electrolysis brine is used which has a content of 20 to 50 g/l of chloride ions and 1 to 7 g/l of ammonia with a pH value of 9.5 to 11.5 and a temperature of 45 to 60°C.